

GRIPTEK ANTI-SLIP SOLUTIONS PTY LTD

26a Production Avenue Kogarah NSW 2217 AUSTRALIA

ABN: 13 622 802 797

T. 1300 01 GRIP E. info@griptek.com.au

Test Report No: 181018C

Slip Resistance Measurement of New Pedestrian Surfaces: AS4586:2013 Appendix A

Client: DW Tiles Pty Ltd - 17 Everley Road, Chester Hill NSW 2162

Test Date: 18/10/2018 Temperature: 22 deg C.

Test Conducted to: AS 4586:2013 Appendix A Conducted by: Sean Murphy

Test Method: Wet Pendulum Testing Test Device: Munro S/N - 1509

Surface: AMZ Amazon Series Rubber Slider Used: Slider 96 (4 S Rubber)

Slider Preparation: Abrasive paper, Grade P400 followed by pink lapping paper wet

Test Location: DW Tiles Pty Ltd - 17 Everley Road, Chester Hill NSW 2162

Surface Preparation: Cleaned with Water & Scrubbing

Surface Application: N/A.

Tested Area:

Specimen Number	Location	Condition	Gradient %	Direction of Test	Mean BPN Last 3 swings
1	Loose Sample	As Found	<2.0	N/A	40
2	Loose Sample	As Found	<2.0	N/A	40
3	Loose Sample	As Found	<2.0	N/A	40
4	Loose Sample	As Found	<2.0	N/A	41
5	Loose Sample	As Found	<2.0	N/A	40

Mean BPN Slip Resistance Value - SRV 40

Classification P3

Contribution to Risk Moderate

The AS 4586 standard provides a guide & recommendation for use, we recommend that this report be read in conjuction with AS 4586 & Handbook HB198: 2014. Refer to Table 3B of HB 198 for requirements of sloped surfaces & ramps. The results in this test do not account for any future wear, contamination or maintenance of this surface. Slipstop Sydney Pty Ltd or our agents, licencees or employees accept no responsibility for any actions whatsoever which may arise as a result of this test report, all information within this report is copyright & is protected by copyright law.

Interpretation of the Wet Pendulum Results					
Classification of pedestrian surface materials according to the AS 4586	Mean BPN				
P5	>54				
P4	45-54				
P3	35-44				
P2	25-34				
P1	12-24				
P0	<12				

Approved Signatory: Michael Holt

tupey