

## Slip Check to AS 4586-2013

### Klif Grey 37,5x75 AF5

**Report Number: R17636g**

**Report Date: 11 December 2018**

**Total Number of Pages 2**

Accredited for compliance with ISO/IEC 17025 – Testing

The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration and inspection reports

#### Issued by

Safe Environments Pty Ltd  
Unit 4, 40 Bessemer Street  
Blacktown NSW 2148  
Australia

#### Prepared for

Atlas Concorde Spa  
Via del Canaletto A41  
41042 Fiorano MO  
Italy

#### Approved by

  
Ryan Voorderhake  
Authorised Signatory

11 December 2018

# Test Report No. R17636g

## Slip Resistance Classification of New Pedestrian Surface Materials

### AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces using specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586 and HB 198.

Requested by: Atlas Concorde Spa  
Client Address: Via del Canaletto A41  
41042 Fiorano MO  
Italy  
Product Manufacturer: Atlas Concorde Spa  
Product Description: Klif Grey 37,5x75 AF5

Test conducted according to: AS 4586:2013 Appendix A  
Location: 4/40 Bessemer Street, Blacktown NSW 2148  
Conducted by: Ola Radzanowska

Date: 29 November 2018  
Sample: Unfixed  
Rubber slider used: Slider 96  
Slope of specimen: Tested on a flat level surface  
Direction of Test: NA

Temperature: 22°C  
Cleaning: None  
Conditioned: Grade P 400 paper dry followed by wet lapping film

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	48	48	51	48	50

<b>Reported SRV of Sample:</b>	<b>49</b>
<b>Class:</b>	<b>P4</b>