

## Slip Check to AS 4586-2013 Navona Surface Tec.

**Report Number: R29693**

**Report Date: 26 September 2023**

**Total Number of Pages 3**

Accredited for compliance with ISO/IEC 17025 – Testing

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration, inspection, proficiency testing scheme providers and reference materials producers reports and certificates

**Issued by**

Safe Environments Pty Limited  
Unit 4, 40 Bessemer Street  
Blacktown NSW 2148

**Prepared for**

DW Tiles  
17 Everley Rd.  
Chester Hill ,NSW 2162

**Approved by**



Nasser Cura  
Authorised Signatory

26 September 2023

# Test Report No. R29693

## Slip Resistance Classification of New Pedestrian Surface Materials

### AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces under specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586, HB 197 & HB 198.

Requested by: DW Tiles  
 Client Address: 17 Everley Rd.  
 Chester Hill ,NSW 2162  
 Product Manufacturer: Supplied by DW Tiles  
 Product Description: Navona Surface Tec.

Test conducted according to: AS 4586:2013 Appendix A  
 Sampling Procedures: Performed by client and tested as received.  
 Location: 4/40 Bessemer Street, Blacktown NSW 2148  
 Conducted by: Ross Abbasi

Date:	25/09/23	Temperature:	22°C
Sample:	Unfixed	Cleaning:	None
Rubber slider used:	Slider 96	Conditioned:	Grade P 400 paper dry followed by wet lapping film
Slope of specimen:	Tested on a flat level surface		
Direction of Test:	NA		

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	51	55	54	48	53

<b>Reported SRV of Sample:</b>	<b>52</b>
<b>Class:</b>	<b>P4</b>

The expanded uncertainty ( $U_{95}$ ) at the 95% level of confidence with a coverage factor (k) of 2 has been estimated to be 3 BPN or 8 %, whichever is the greater; sampling uncertainty has not been included. The expanded uncertainty should be considered when interpreting results or assessing conformity. Results relate only to items tested.

This test report shall not be reproduced unless in full, without written approval of Safe Environments Pty Ltd

26 September 2023

# Test Report No. R29693

## Accelerated Wear Slip Resistance Test


**AS 4586-2013 Appendix A: incorporating accelerated wear conditioning to evaluate in-service wear**

The purpose of the accelerated wear condition is to assist specifiers to better understand how the slip resistance of an individual product may alter with wear, thus helping to differentiate between products that might otherwise have seemingly similar slip resistance characteristics. AS 4586 does not provide guidance on the conduct of such accelerated wear tests; however, Appendix A3 states that “if a product Standard or specification contains a requirement for the permanence of slip resistance, this requirement shall be determined after the appropriate accelerated again or wear testing procedure”. The conditioning protocol primarily used within industry is based on method developed by Strautins<sup>1</sup>. The results are intended to be used as an informative guide to the selection of surfaces within a quality management system; please refer to AS 4586, HB 198 and Strautins (2008) for further information.

Test Method:	AS 4586 Appendix A:		
	Test sample description, operating and equipment parameters outlined on previous page		
Sample Preparation:	Safe Environments in-house <i>SOP – Accelerated Wear Slip Testing</i>		
Abrasive pad:	3M Scotchbrite Heavy Duty Scour Pad No. 86 (water wet)		
Machine	Gardco D12VFI washability and wear-testing machine		
Mass of friction boat:	1000 ±50g	Area:	100 ±10mm x 100 ±10mm
Cycle Rate:	50 ±5 cycles per min	Path length:	300 ±50 mm

Wear Cycles	Specimen 2	Specimen 4	Specimen 5	Mean	Class
0	55	48	53	52	P4*
100	52	45	47	48	P4*
500	45	39	41	42	P3*
1000	44	38	38	40	P3*
5000	42	35	39	39	P3*

**BPN vs Wear Cycles**



<sup>1</sup> Strautins, Carl J (2008) ‘Sustainable Slip Resistance: An Opportunity for Innovation’, Qualicer ’08, Xth World Congress on Ceramic Tile Quality, Castellon Spain. Publication available upon request.

\*The classification is indicative only.