

			E. info@griptek.com.au
Test Report No:	160120G		- 0 1
Slip Resistance Measurement of	New Pedestrian Surfaces: AS4586:2	2013 Appendix A	
Client:	DW Tiles Pty Ltd - 17 Everley Road, 0	Chester Hill NSW 2162	
Test Date:	16/01/2020	Temperature:	25 Deg C.
Test Conducted to:	AS 4586:2013 Appendix A	Conducted by:	Sebastian Silva
Test Method:	Wet Pendulum Testing	Test Device:	Munro S/N - 1509
Surface:	Panama External	Rubber Slider Used:	Slider 96 (4 S Rubber)
Slider Preparation:	Abrasive paper, Grade P400 followed	l by pink lapping paper v	vet
Test Location:	DW Tiles Pty Ltd - 17 Everley Road, 0	Chester Hill NSW 2162	
Surface Preparation:	Cleaned with Water & Scrubbing		
Surface Application:	N/A.		

Tested Area:

Specimen Number	Location	Condition	Gradient %	Direction of Test	Mean BPN Last 3 swings
1	Loose Sample	As Found	<2.0	N/A	57
2	Loose Sample	As Found	<2.0	N/A	58
3	Loose Sample	As Found	<2.0	N/A	58
4	Loose Sample	As Found	<2.0	N/A	60
5	Loose Sample	As Found	<2.0	N/A	58

## Mean BPN Slip Resistance Value - SRV 58

Classification P5

Contribution to Risk Very Low

The AS 4586 standard provides a guide & recommendation for use,
we recommend that this report be read in conjuction with AS 4586
& Handbook HB198: 2014. Refer to Table 3B of HB 198 for
requirements of sloped surfaces & ramps. The results in this test
do not account for any future wear, contamination or maintenance
of this surface. Slipstop Sydney Pty Ltd or our agents, licencees or
employees accept no responsibility for any actions whatsoever
which may arise as a result of this test report, all information within
this report is copyright & is protected by copyright law.

Interpretation of the Wet Pendulum Results				
Classification of pedestrian surface materials according to the AS 4586	Mean BPN			
P5	>54			
P4	45-54			
P3	35-44			
P2	25-34			
P1	12-24			
P0	<12			

Approved Signatory: Michael Holt

terper