

## **GRIPTEK ANTI-SLIP SOLUTIONS PTY LTD**

26a Production Avenue Kogarah NSW 2217 AUSTRALIA

ABN: 13 622 802 797 **T. 1300 01 GRIP** 

E. info@griptek.com.au

Test Report No: 240822A

Slip Resistance Measurement of New Pedestrian Surfaces: AS4586:2013 Appendix A

Client: DW Tiles Pty Ltd - 17 Everley Road, Chester Hill NSW 2162

**Test Date**: 24/08/2022 **Temperature**: 17 Deg C.

Test Conducted to: AS 4586:2013 Appendix A Conducted by: Sean C Murphy

B.A (Syd. U), Dip. Ed

**Test Method:** Wet Pendulum Testing **Test Device:** Munro - Reg. No 2015 Calibration No. AU21/104

Surface: Yosemite Fiammata Rubber Slider Used: Slider 96 (4 S Rubber)

Slider Preparation: Abrasive paper, Grade P400 followed by pink lapping paper wet

**Test Location:** 17 Everley Road, Chester Hill NSW 2162

Surface Preparation: Cleaned with Water & Scrubbing

Surface Application: N/A

## Tested Area:

Specimen	Location	Condition	Gradient	Direction of Test	Mean BPN
Number			%		Last 3 swings
1	Loose Sample	As Found	<2.0	N/A	54
2	Loose Sample	As Found	<2.0	N/A	51
3	Loose Sample	As Found	<2.0	N/A	53
4	Loose Sample	As Found	<2.0	N/A	53
5	Loose Sample	As Found	<2.0	N/A	52

Mean BPN Slip Resistance Value - SRV 53

P4

Classification

Interpretation of the Wet Pendulum Results					
Classification of pedestrian surface materials according to the AS 4586	Mean BPN				
P5	>54				
P4	45-54				
P3	35-44				
P2	25-34				
P1	12-24				
P0	<12				

Approved Signatory: Michael Holt

The AS 4586 standard provides a guide & recommendation for use, we recommend that this report be read in conjuction with AS 4586 & Handbook HB198: 2014. Refer to Table 3B of HB 198 for requirements of sloped surfaces & ramps. The results in this test do not account for any future wear, contamination or maintenance of this surface. GripTek Anti-Slip Solutions Pty Ltd or our agents, licencees or employees accept no responsibility for any actions whatsoever which may arise as a result of this test report, all information within this report is copyright & is protected by copyright law.